


GENIOSIL[®] IOTE

GENIOSIL[®]

Silanes

GENIOSIL[®] IOTE is a mixture of octyltriethoxysilanes isomers, with iso-octyltriethoxysilane as the main component.

GENIOSIL[®] IOTE is used in undiluted form for the hydrophobic priming and impregnation of concrete and reinforced concrete. In addition, GENIOSIL[®] IOTE is suitable for the hydrophobic treatment of fillers and pigments.



CAS No. 35435-21-3 | Empirical formula $C_{14}H_{32}O_3Si$ | Molecular weight 276,0 g/mol

Properties

GENIOSIL[®] IOTE is characterized by:

- Excellent penetrating power
- no solvents, environmentally compatible
- low volatility

Treated concrete will have the following permanent properties:

- dramatic reduction in chloride and water absorption
- no loss in breathability
- improved durability against freeze-thaw de-icing salt stress
- enhanced durability
- provides good adhesion for paints

In the construction material GENIOSIL[®] IOTE reacts with atmospheric moisture and / or the water in the building material's pores, eliminating alcohol. The active thus substance formed greatly reduces the concrete's absorbency in the active zone (penetration depth after post treatment), but without blocking any pores or capillaries. The impregnated building material retains very high water-vapor permeability.

Technical data

General Characteristics

Property	Condition	Value	Method
Boiling point	1013 hPa	239 °C	not specified
Density	25 °C	0.87 g/cm ³	DIN 51757
Flash point	-	65 °C	ISO 3679
Ignition temperature	-	259 °C	EN 14522
Vapour pressure	25 °C	0.05 hPa	EU-GL.A.4
Viscosity, dynamic	25 °C	2.0 mPa·s	DIN 51562

These figures are only intended as a guide and should not be used in preparing specifications.

All the information provided is in accordance with the present state of our knowledge. Nonetheless, we disclaim any warranty or liability whatsoever and reserve the right, at any time, to effect technical alterations. The information provided, as well as the product's fitness for an intended application, should be checked by the buyer in preliminary trials. Contractual terms and conditions always take precedence. This disclaimer of warranty and liability also applies particularly in foreign countries with respect to third parties' rights.

Applications

- Adhesives
- Building & Construction Adhesives
- Chemical Industry
- Composites
- Industrial Adhesives
- Industrial Coatings
- Primers for Paints & Coatings
- Sealants
- Thermoplastics & Elastomers

Application details

Applications

- Concrete Protection
- Construction Materials
- Fiber Cement Boards
- Hydrophobic Impregnation
- Infrastructure

The work performed (preparing the concrete surface, setting up a reference surface, application and quality control) must follow the applicable regulations (in Germany these are the DAfStb repair work guidelines and the ZTV-ING).

- Concrete should not be impregnated until at least four weeks after it has been produced so that the setting of the cement is not affected.

- New surfaces that are still unsoiled must be cleansed of coarse particles and dust deposits by sweeping or, if necessary, using compressed air. Surfaces already weathered, and those heavily soiled by oil, rubber residue, etc., must first be cleaned using superheated steam or high-pressure water before commencing treatment. It is imperative that the water used be siphoned off immediately to prevent saturation of the concrete.

- Impregnation should always be performed on superficially dry concrete, i.e., when the surface of the concrete appears evenly dry, no more damp patches are visible, and the moisture content equilibrium is established. To this end, moisture in the surface zone of the concrete is measured using a suitable technique (CM method or other methods allowed under ZTV-ING). The surface-zone moisture content of the concrete (from the surface to a depth of 20 mm) should not exceed 4 wt. %.

- Evenly apply the impregnating agent to the building material in several coats, wet-on-wet. Do not allow puddles to form. The impregnating agent is applied by flow coating at reduced pressure. A lambskin roller may be used afterward for more even coverage.

- In the event of unexpected rain, cover surfaces already impregnated and halt all further impregnation.

- GENIOSIL® IOTE should never come in direct contact with bitumen. The resistance of insulating materials to GENIOSIL® IOTE must be tested on a case-by-case basis for the required temperatures.

GENIOSIL® IOTE is recommended for the hydrophobic impregnation and priming of concrete and reinforced concrete in road, bridge and building construction. In addition it is suitable for the hydrophobic treatment of fillers and pigments.

Expert opinions:

The effectiveness of GENIOSIL® IOTE is confirmed and documented in the following laboratory reports:

- Polymer Institut Dr. Stenner GmbH, Flörsheim, Germany

Test report P 5024-1, May 14, 2007; EN 1504-2

Test report No. P 1637, Nov. 6, 1998; TL/TP OS (1996 issue) of ZTV-SIB 90

- CBI Betonginstitutet AB, Borås, Sweden

Test report No. 2297156 A, Sept. 6, 1996; BRO 94

Test report No. P701959 B, Oct. 19, 2007; BRO 2004

Test report No. FX00045B, Jan. 27, 2011; WVAMA

Anläggning 09 rev. 2

Test report No. 6P00354 B, NT BUILD 515

- VTT Technical Research Center of Finland, Helsinki, Finland

Test report VTT-R-42523-11, Apr. 6, 2011; SILKO 2010

- TRL Ltd., Berkshire, UK

Report PR/CSS/34/03, Aug. 2003; BD43/03

Report PPR 362, Oct. 2009; BD 43/03

- CTL, Ltd, Skokie, Illinois, USA

Project No. 406945; Jan. 5, 2004; AASHTO T259/T260

Project No. 406945; Aug. 8, 2003; ASTM C 672-98

Project No. 406945; June 23, 2003; ASTM E 514-92

- AMEC Earth & Environmental, Edmonton, Canada Project No. EA 15621;

Dec. 12, 2005; BT-001

Packaging and storage

Packaging

800 KG IBC
180 KG Drum
25 KG Pail

Storage

The containers must be protected against sunlight. The 'Best use before end' date of each batch is shown on the product label. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety notes

Comprehensive instructions are given in the corresponding Material Safety Data Sheets. They are available on request from WACKER subsidiaries or may be printed via WACKER web site <http://www.wacker.com>.

QR Code GENIOSIL® IOTE



For technical, quality or product safety questions, please contact:

Wacker Chemie AG, Hanns-Seidel-Platz 4, 81737 Munich, Germany
productinformation@wacker.com, www.wacker.com

The data presented in this medium are in accordance with the present state of our knowledge but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this medium should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The information provided by us does not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose.