









Adipate Esters

Product	TruVis A - 80	TruVis A - 85	TruVis A - 90	TruVis A - 100	TruVis A - 130
 Property					
 Appearance, Clear/FSM	Pass	Pass	Pass	Pass	Pass
 Purity, Ester Content, % (min)	99.0	99.0	99.0	99.0	99.0
 Color, Pt/Co (max)	50	50	50	75	100
 Moisture, ppm (max)	500	500	500	500	350
 Acid Value, mg KOH/gm (max)	0.05	0.05	0.05	0.05	0.05
ρ Spec. Grav. @20°C	0.925 - 0.929	0.926 - 0.932	0.919 - 0.925	0.915 - 0.919	0.913 - 0.916
 Visc. cSt @ 40°C	7.6 - 8.8	8.5 - 10.4	10.8 - 12.6	13.0 - 15.0	25.5 - 29.0
 Visc. cSt @ 100°C	2.1 - 2.5	2.5 - 2.9	2.9 - 3.4	3.3 - 3.6	5.1 - 5.5
 Viscosity Index	88	144	137	146	153
 Flash Point, COC, °C (min)	195	191	195	216	220
 Pour Point, °C (max)	-67	-67	-45	-55	-54
 Sediment, insoluble contamination, mg/L (max)	3.5	3.5	3.5	3.5	3.5
 NOACK Volatility D-5800	43.03	33.07	22.80	15.01	6.81
 Hydrolytic Stability D-2619 mg KOH / gm	+0.09	+0.09	+0.01	+0.08	+0.00

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. It is provided for informational purposes only, and is not intended to constitute a sales specification. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.

www.TruVisEsters.com

 **TEKNORAPEX**

Teknor Apex Company
 Chemicals Division
 500 Central Avenue
 Pawtucket, RI 02861
 1-800-554-9887
truvis@teknorapex.com